

Rigidur flooring element 30 HF



- can be fitted with all common floor coverings
- can be used in residential rooms with moisture levels



- ecological certified and recommended
- easy and quick to prepare and lay




- no moisture means no need for drying time
- a complete system for a safe installation
- the lowest height in comparison with other types of screed



- proven system with regard to sound- and heat insulation
- low weight makes them well-suited on ceilings with low load-bearing capacities

Characteristics	The Rigidur Flooring Element consists of two factory-joined fibreboards with step rabbet and a laminated wood fibre soundinsulation- board. Rigidur Flooring elements are undercoat- varnished by factory.
Application	The Rigidur Flooring Element HF is universally applicable as dry screed for reconstruction and renovation purposes, in old and new buildings and for special fire protection needs in the office and administration area.
Installation	According to Rigidur installation guide.

Technical data

Type	fibreboards from reprocessing	as per DIN EN 14190			
	normally inflammable European Classification: E	as per DIN EN 13051-1			
Edge profile	Edges		step rabbet		
	Element joint	stepped joint of 50 mm			
Dimensions	Nominal thickness	30	[mm]		
		2 x 10 GF+ 1x10 HF	[mm]		
	Width x Lengths	500 x 1500	[mm]	In case of cutting the elements please take care of the 2 fixing staples.	
	Dimensional tolerances	Thickness	±1.0	[mm]	referring to DIN EN 15283-2
		Width	-2/+0	[mm]	
Length		-2/+0	[mm]		
Squareness: deviation per m width		≤ 2.0	[mm/m]		

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.

Rigidur flooring element 30 HF

Rigidur flooring element 30 HF				
Plasterboard marking	On top side	The marking in longitudinal direction in black contains:		
		<ul style="list-style-type: none"> - RIGIDUR EE 30 HF - CE-marking - DIN EN 14190 fire resistance as per DIN EN 13051-1 - E - Production date and -time 		
Plasterboard marking	Palette poster	Every pallet is signed by a palette poster with article-code. It contains:		
		<ul style="list-style-type: none"> - Rigidur Estrichelement 30 HF - CE-marking - dimensions - weight - elements per palette - storage instructions 		
Weight	Weight per unit area	ca. 26.1	[kg/m ²]	referring to DIN EN 15283-2
Strengths	Surface hardness	35	[N/mm ²]	as per DIN EN ISO 6506-1
	Point load	≤4.0	[kN]	referring to DIN EN 1991-1- 1/NA:2010-12
Heat	Thermal dilatation	0.015	[mm/(m x K)]	referring to DIN EN 318
	Heat transfer resistance R	0.295	[(m ² x K)/W]	as per DIN EN 12667
	Thermal threshold stress (long-term load)	max. 50	[°C]	short-term load 60°C
Humidity	Vapour diffusion resistance factor μ	GF: 19 HF: 5	[-]	as per DIN EN ISO 12572
	Dilatation due to changing of relative humidity by 30% (20°C)	0.045	[%]	referring to DIN EN 318
	Stable moisture content at 20°C, 65% relative humidity approx.	1-1.3	[%]	as per DIN EN 322
Sign	The values given in this product data sheet solely describe the performance characteristics of the products. Rigips-Systems also have far-reaching structural-physical and static properties, which can be found in our system documentation (e.g. Planen und Bauen).			

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.