

## Rigips Bauplatte RB 9,5



- flexible and space saving
- individual room layout



- extended durability
- excellent ecobalance






- agreeable inside air humidity
- recommended by the IBR Rosenheim



- cost-effective due to short construction time
- no long drying times





<b>Characteristics</b>	Rigips Bauplatten (plasterboards) are made of a special gypsum core encased in cardboard.
<b>Application</b>	Rigips Bauplatten (plasterboards) are an ideal solution to build up drywalls, installation walls, suspended ceilings, sloping ceilings and many other applications.
<b>Installation</b>	According to the Rigips application guidance

### Technical data

<b>Type</b>	Gypsum plasterboard type A				as per DIN EN 520	
	Gypsum plasterboard GKB				as per DIN 18180	
	non-combustible				as per DIN EN 520	
	European Classification: A2-s1, d0 (B)					
<b>Edge profile</b>	Longitudinal edges		Vario			
		Designed for filling of joints with Rigips VARIO joint filler, either with or without reinforcing strips.				
	Transverse edges		SK		SKF	
<b>Dimensions</b>	Nominal thickness	9.5	[mm]			
	Width x Lengths	For possible dimensions please consult our delivery programme. Special lengths (intermediate sizes, overlength) and sheet cutting possible - delivery time on request.				
	Dimensional tolerances	Thickness	±0.5	[mm]		
		Width	+0/-4	[mm]		
Length		+0/-5	[mm]			
Squareness: deviation per m width		≤ 2.5	[mm/m]	as per DIN EN 520		

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.

## Rigips Bauplatte RB 9,5

Rigips Bauplatte RB 9,5					
Plasterboard marking	On rear side	The marking in longitudinal direction in blue contains: - RIGIPS Bauplatte RB - CE-symbol - DIN EN 520: type A - DIN 18180: GKB - A2-s1, d0 (B) - Production date and/or shift number  Generally, together with the lettering, a row of dots mark the board centre within a strip of ca. 5 cm width (position of the metal stud sections for walls).			
	On front side	To ease installation, the board centre is marked with the letters RB which are 3-5mm high and located at a distance of about 250 mm (screw spacing) from each other. The position tolerance of the marking from the board centre is $\pm 2$ cm max.			
	Edge marking	„RIGIPS VARIO 9,5“ at the longitudinal edge in blue			
Weight	Weight per unit area	$\geq 6.5$	[kg/m <sup>2</sup> ]	as per DIN 18180	
	Apperent density	$\geq 685$	[kg/m <sup>3</sup> ]	as per DIN EN 520	
Strengths	Breaking load	$\perp$ perpendicular to direction of manufacture in longitudinal direction of the board			as per DIN EN 520 as per DIN 18180
		$\geq 410$	$\perp$ [N]		
	$\geq 160$	$\parallel$ [N]			
	$\parallel$ parallel to direction of manufacture in transverse direction of the board			as per DIN EN 520 as per DIN 18180	
	Bending tensile strength	$\geq 8.0$	$\perp$ [N/mm <sup>2</sup> ]		
		$\geq 3.1$	$\parallel$ [N/mm <sup>2</sup> ]		
	Modulus of elasticity	$\geq 2500$	$\perp$ [N/mm <sup>2</sup> ]		
	$\geq 2000$	$\parallel$ [N/mm <sup>2</sup> ]			
Compressive strength vertical to the surface	5-10	[N/mm <sup>2</sup> ]			
Tensile strength	1.8-2.5	[N/mm <sup>2</sup> ]			
	in longitudinal direction of the board				
	1.0-1.2	[N/mm <sup>2</sup> ]			
	in transverse direction of the board				
Shear strength	NPD	[N]	connection between board and substructure	as per DIN EN 520	
Shear strength	3.0-4.5	[N/mm <sup>2</sup> ]	vertical to surface		
	2.5-4.0	[N/mm <sup>2</sup> ]	parallel to surface		

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.

## Rigips Bauplatte RB 9,5

Heat	Thermal conductivity $\lambda_R$	0.25	[W/(m x K)]	as per DIN EN 520
	Thermal expansion coefficient at 60% RH	0.013-0.020	[mm/(m x K)]	
	Thermal threshold stress (long-term load)	max. 50	[°C]	short-term load 60°C
Humidity	Vapour diffusion resistance factor $\mu$	dry 10 wet 4	[-] [-]	as per DIN EN 520
	Diffusion equivalent air layer thickness $s_d$	dry 0.10 wet 0.04	[m] [m]	as per DIN 4108
	Dilatation due to changing of relative humidity by 30% (20°C)	0.015	[%]	
Sign	The values given in this product data sheet solely describe the performance characteristics of the products. Rigips-Systems also have far-reaching structural-physical and static properties, which can be found in our system documentation (e.g. Planen und Bauen).			

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.